



Technical Data Sheet¹

Material	FX 240
Polymer	Modified Olefin
Melting Range	100-110°C
Melt Index 190°C 2.16 kg	9 - 11

Fusing Conditions: (Guideline)

Temperature	130-145°C
Time	10-15 seconds
Pressure	2-5 bar
Washable to	60°C
Dry-clean Resistance	Fair

Typical applications:

General lamination of various substrates including woven and non woven textiles, foam, glass fibre and metals

¹ Our only obligation shall be to replace or pay for any material proved defective. Beyond the purchase price of materials supplied by us we assume no liability for damages of any kind and the user accepts the product "as is" and without Warranties expressed or implied. The suitability of the product for an intended use shall be solely up to the user and checked by them under recommended conditions.